

ISSN 2518-170X (Online),
ISSN 2224-5278 (Print)

ҚАЗАҚСТАН РЕСПУБЛИКАСЫ
ҰЛТТЫҚ ҒЫЛЫМ АКАДЕМИЯСЫНЫҢ
Қ. И. Сәтпаев атындағы Қазақ ұлттық техникалық зерттеу университеті

Х А Б А Р Л А Р Ы

ИЗВЕСТИЯ

НАЦИОНАЛЬНОЙ АКАДЕМИИ НАУК
РЕСПУБЛИКИ КАЗАХСТАН
Қазақстан Республикасының Ғылым Академиясының
Қ. И. Сәтпаев атындағы Қазақ ұлттық техникалық зерттеу университеті

NEWS

OF THE ACADEMY OF SCIENCES
OF THE REPUBLIC OF KAZAKHSTAN
Kazakh national research technical university
named after K. I. Satpayev

**SERIES
OF GEOLOGY AND TECHNICAL SCIENCES**

1 (433)

JANUARY – FEBRUARY 2019

THE JOURNAL WAS FOUNDED IN 1940

PUBLISHED 6 TIMES A YEAR

ALMATY, NAS RK

NAS RK is pleased to announce that News of NAS RK. Series of geology and technical sciences scientific journal has been accepted for indexing in the Emerging Sources Citation Index, a new edition of Web of Science. Content in this index is under consideration by Clarivate Analytics to be accepted in the Science Citation Index Expanded, the Social Sciences Citation Index, and the Arts & Humanities Citation Index. The quality and depth of content Web of Science offers to researchers, authors, publishers, and institutions sets it apart from other research databases. The inclusion of News of NAS RK. Series of geology and technical sciences in the Emerging Sources Citation Index demonstrates our dedication to providing the most relevant and influential content of geology and engineering sciences to our community.

Қазақстан Республикасы Ұлттық ғылым академиясы "ҚР ҰҒА Хабарлары. Геология және техникалық ғылымдар сериясы" ғылыми журналының Web of Science-тің жаңаланған нұсқасы Emerging Sources Citation Index-те индекстелуге қабылданғанын хабарлайды. Бұл индекстелу барысында Clarivate Analytics компаниясы журналды одан әрі the Science Citation Index Expanded, the Social Sciences Citation Index және the Arts & Humanities Citation Index-ке қабылдау мәселесін қарастыруда. Web of Science зерттеушілер, авторлар, баспашылар мен мекемелерге контент тереңдігі мен сапасын ұсынады. ҚР ҰҒА Хабарлары. Геология және техникалық ғылымдар сериясы Emerging Sources Citation Index-ке енуі біздің қоғамдастық үшін ең өзекті және беделді геология және техникалық ғылымдар бойынша контентке адалдығымызды білдіреді.

НАН РК сообщает, что научный журнал «Известия НАН РК. Серия геологии и технических наук» был принят для индексирования в Emerging Sources Citation Index, обновленной версии Web of Science. Содержание в этом индексировании находится в стадии рассмотрения компанией Clarivate Analytics для дальнейшего принятия журнала в the Science Citation Index Expanded, the Social Sciences Citation Index и the Arts & Humanities Citation Index. Web of Science предлагает качество и глубину контента для исследователей, авторов, издателей и учреждений. Включение Известия НАН РК. Серия геологии и технических наук в Emerging Sources Citation Index демонстрирует нашу приверженность к наиболее актуальному и влиятельному контенту по геологии и техническим наукам для нашего сообщества.

Б а с р е д а к т о р ы
э. ғ. д., профессор, ҚР ҰҒА академигі

И.К. Бейсембетов

Бас редакторының орынбасары

Жолтаев Г.Ж. проф., геол.-мин. ғ. докторы

Р е д а к ц и я а л қ а с ы:

Абаканов Т.Д. проф. (Қазақстан)
Абишева З.С. проф., академик (Қазақстан)
Агабеков В.Е. академик (Беларусь)
Алиев Т. проф., академик (Әзірбайжан)
Бакиров А.Б. проф., (Қырғыстан)
Беспаев Х.А. проф. (Қазақстан)
Бишимбаев В.К. проф., академик (Қазақстан)
Буктуков Н.С. проф., академик (Қазақстан)
Булат А.Ф. проф., академик (Украина)
Ганиев И.Н. проф., академик (Тәжікстан)
Грэвис Р.М. проф. (АҚШ)
Ерғалиев Г.К. проф., академик (Қазақстан)
Жуков Н.М. проф. (Қазақстан)
Қожахметов С.М. проф., академик (Қазақстан)
Конторович А.Э. проф., академик (Ресей)
Курскеев А.К. проф., академик (Қазақстан)
Курчавов А.М. проф., (Ресей)
Медеу А.Р. проф., академик (Қазақстан)
Мұхамеджанов М.А. проф., корр.-мүшесі (Қазақстан)
Нигматова С.А. проф. (Қазақстан)
Оздоев С.М. проф., академик (Қазақстан)
Постолатий В. проф., академик (Молдова)
Ракишев Б.Р. проф., академик (Қазақстан)
Сейтов Н.С. проф., корр.-мүшесі (Қазақстан)
Сейтмуратова Э.Ю. проф., корр.-мүшесі (Қазақстан)
Степанец В.Г. проф., (Германия)
Хамфери Дж.Д. проф. (АҚШ)
Штейнер М. проф. (Германия)

«ҚР ҰҒА Хабарлары. Геология мен техникалық ғылымдар сериясы».

ISSN 2518-170X (Online),

ISSN 2224-5278 (Print)

Меншіктенуші: «Қазақстан Республикасының Ұлттық ғылым академиясы» РҚБ (Алматы қ.).

Қазақстан республикасының Мәдениет пен ақпарат министрлігінің Ақпарат және мұрағат комитетінде
30.04.2010 ж. берілген №10892-Ж мерзімдік басылым тіркеуіне қойылу туралы куәлік.

Мерзімділігі: жылына 6 рет.

Тиражы: 300 дана.

Редакцияның мекенжайы: 050010, Алматы қ., Шевченко көш., 28, 219 бөл., 220, тел.: 272-13-19, 272-13-18,
<http://www.geolog-technical.kz/index.php/en/>

© Қазақстан Республикасының Ұлттық ғылым академиясы, 2019

Редакцияның Қазақстан, 050010, Алматы қ., Қабанбай батыра көш., 69а.

мекенжайы: Қ. И. Сәтбаев атындағы геология ғылымдар институты, 334 бөлме. Тел.: 291-59-38.

Типографияның мекенжайы: «Аруна» ЖК, Алматы қ., Муратбаева көш., 75.

Г л а в н ы й р е д а к т о р
д. э. н., профессор, академик НАН РК

И. К. Бейсембетов

Заместитель главного редактора

Жолтаев Г.Ж. проф., доктор геол.-мин. наук

Р е д а к ц и о н н а я к о л л е г и я:

Абаканов Т.Д. проф. (Казахстан)
Абишева З.С. проф., академик (Казахстан)
Агабеков В.Е. академик (Беларусь)
Алиев Т. проф., академик (Азербайджан)
Бакиров А.Б. проф., (Кыргызстан)
Беспаяев Х.А. проф. (Казахстан)
Бишимбаев В.К. проф., академик (Казахстан)
Буктуков Н.С. проф., академик (Казахстан)
Булат А.Ф. проф., академик (Украина)
Ганиев И.Н. проф., академик (Таджикистан)
Грэвис Р.М. проф. (США)
Ергалиев Г.К. проф., академик (Казахстан)
Жуков Н.М. проф. (Казахстан)
Кожаметов С.М. проф., академик (Казахстан)
Конторович А.Э. проф., академик (Россия)
Курскеев А.К. проф., академик (Казахстан)
Курчавов А.М. проф., (Россия)
Медеу А.Р. проф., академик (Казахстан)
Мухамеджанов М.А. проф., чл.-корр. (Казахстан)
Нигматова С.А. проф. (Казахстан)
Оздоев С.М. проф., академик (Казахстан)
Постолатий В. проф., академик (Молдова)
Ракишев Б.Р. проф., академик (Казахстан)
Сейтов Н.С. проф., чл.-корр. (Казахстан)
Сейтмуратова Э.Ю. проф., чл.-корр. (Казахстан)
Степанец В.Г. проф., (Германия)
Хамфери Дж.Д. проф. (США)
Штейнер М. проф. (Германия)

«Известия НАН РК. Серия геологии и технических наук».

ISSN 2518-170X (Online),

ISSN 2224-5278 (Print)

Собственник: Республиканское общественное объединение «Национальная академия наук Республики Казахстан (г. Алматы)

Свидетельство о постановке на учет периодического печатного издания в Комитете информации и архивов Министерства культуры и информации Республики Казахстан №10892-Ж, выданное 30.04.2010 г.

Периодичность: 6 раз в год

Тираж: 300 экземпляров

Адрес редакции: 050010, г. Алматы, ул. Шевченко, 28, ком. 219, 220, тел.: 272-13-19, 272-13-18,
<http://nauka-nanrk.kz/geology-technical.kz>

© Национальная академия наук Республики Казахстан, 2019

Адрес редакции: Казахстан, 050010, г. Алматы, ул. Кабанбай батыра, 69а.

Институт геологических наук им. К. И. Сатпаева, комната 334. Тел.: 291-59-38.

Адрес типографии: ИП «Аруна», г. Алматы, ул. Муратбаева, 75

E d i t o r i n c h i e f

doctor of Economics, professor, academician of NAS RK

I. K. Beisembetov

Deputy editor in chief

Zholtayev G.Zh. prof., dr. geol-min. sc.

E d i t o r i a l b o a r d:

Abakanov T.D. prof. (Kazakhstan)
Abisheva Z.S. prof., academician (Kazakhstan)
Agabekov V.Ye. academician (Belarus)
Aliyev T. prof., academician (Azerbaijan)
Bakirov A.B. prof., (Kyrgyzstan)
Bespayev Kh.A. prof. (Kazakhstan)
Bishimbayev V.K. prof., academician (Kazakhstan)
Buktukov N.S. prof., academician (Kazakhstan)
Bulat A.F. prof., academician (Ukraine)
Ganiyev I.N. prof., academician (Tadjikistan)
Gravis R.M. prof. (USA)
Yergaliev G.K. prof., academician (Kazakhstan)
Zhukov N.M. prof. (Kazakhstan)
Kozhakhmetov S.M. prof., academician (Kazakhstan)
Kontorovich A.Ye. prof., academician (Russia)
Kurskeyev A.K. prof., academician (Kazakhstan)
Kurchavov A.M. prof., (Russia)
Medeu A.R. prof., academician (Kazakhstan)
Muhamedzhanov M.A. prof., corr. member. (Kazakhstan)
Nigmatova S.A. prof. (Kazakhstan)
Ozdoiyev S.M. prof., academician (Kazakhstan)
Postolatii V. prof., academician (Moldova)
Rakishev B.R. prof., academician (Kazakhstan)
Seitov N.S. prof., corr. member. (Kazakhstan)
Seitmuratova Ye.U. prof., corr. member. (Kazakhstan)
Stepanets V.G. prof., (Germany)
Humphery G.D. prof. (USA)
Steiner M. prof. (Germany)

News of the National Academy of Sciences of the Republic of Kazakhstan. Series of geology and technology sciences.

ISSN 2518-170X (Online),

ISSN 2224-5278 (Print)

Owner: RPA "National Academy of Sciences of the Republic of Kazakhstan" (Almaty)

The certificate of registration of a periodic printed publication in the Committee of information and archives of the Ministry of culture and information of the Republic of Kazakhstan N 10892-Ж, issued 30.04.2010

Periodicity: 6 times a year

Circulation: 300 copies

Editorial address: 28, Shevchenko str., of. 219, 220, Almaty, 050010, tel. 272-13-19, 272-13-18,
<http://nauka-nanrk.kz/geology-technical.kz>

© National Academy of Sciences of the Republic of Kazakhstan, 2019

Editorial address: Institute of Geological Sciences named after K.I. Satpayev
69a, Kabanbai batyr str., of. 334, Almaty, 050010, Kazakhstan, tel.: 291-59-38.

Address of printing house: ST "Aruna", 75, Muratbayev str, Almaty

NEWS

OF THE NATIONAL ACADEMY OF SCIENCES OF THE REPUBLIC OF KAZAKHSTAN

SERIES OF GEOLOGY AND TECHNICAL SCIENCES

ISSN 2224-5278

Volume 1, Number 433 (2019), 32 – 37

<https://doi.org/10.32014/2019.2518-170X.3>

UDC 669.181

MRNTI 53.31.15/53.31.17

S. Tleugabulov¹, D. Ryzhonkov², N. Aytbayev³, G. Koishina¹, G. Sultamurat³

¹Kazakh National Research Technical University named after K. I. Satpayev (Satpayev University),
Almaty, Kazakhstan,

²National University of Science and Technology (MISIS), Moscow, Russia,

³Karaganda State Technical University, Karaganda, Kazakhstan.

E-mail: suleiman_70@mail.ru, diryzhonkov@mail.ru, nurlan_2303@mail.ru,
gulzada.koishina@mail.ru, sultamurat_gi@mail.ru

THE REDUCTION SMELTING OF METAL-CONTAINING INDUSTRIAL WASTES

Abstract. Metal containing scrape accumulation is not only issue of the ecological safety of regions, but is a new paradigm in development of the black metallurgy (direct production of iron) obtaining the energy and resources conservation policy.

The purpose of the work: use of metal-containing and carbon-containing industrial waste – converter sludge and coal sludge of the JSC "ArcelorMittal Temirtau" metallurgical enterprise.

The process structuring chain consists of: 1) ore-coal mixture conditioning from converter and coal slimes; 2) production of ore-coal pellets from the fine ore-coal mixture; 3) metallization of ore-coal pellets; 4) reduction smelting of metallized pellets and production of natural-alloyed steel.

The solid carbon was used as a reducing agent, while preparing the ore-coal mixture we adhere to the principle of complete reduction of the net extracted iron and manganese metals. Therefore, the stoichiometric consumption of prepared coal sludge per unit of iron ore concentrate was determined according to the developed procedure, taking into account the sequentially phase transformation of oxides. As a result of performed calculations, the coal feed rate per unit of concentrate in the amount of 0,265 kg/kg was obtained. The ore-coal mixture consisted of the sum of prepared converter and coal sludges.

On the basis of metal- and carbon-containing sludge of JSC "ArcelorMittal Temirtau" the ore pelletized pellets with stoichiometric carbon content are obtained. Sequential processing, drying, metallization and reduction smelting made it possible to obtain metal ingots corresponding to high-quality steel in composition in the final stage.

Key words: metal-containing waste, converter sludge, coal sludge, metallization, pellets, steel, carbon, phosphorus, reduction, smelting, crystallization.

The conventional technology of metallurgical production of cast iron and steel is based on the two-stage complex "Blast furnace-Converter". At the initial stage of the complex, conventionally, agglomerate oxide materials are used as raw materials in the form of sinter and pellets in predetermined weight ratios to the mass of coke. The mass fraction of coke in the charge provides the thermal balance of the reduction smelting process as a source of hot reducing gases (HRG) used to heat the charge column and to reduce iron, and also to melt the ore portion of the charge.

In addition, the coke layer plays an important role as a nozzle in which counterflow filtration of HRG and melts is realized, as well as a source of direct reduction of iron and hard-to-reduce metals by solid carbon. As can be seen, under the conditions of implementation of the reduction-smelting process in the blast furnace there is a stable excess of coke and the melted metal product is cast iron.

In view of high performance of blast furnaces, the worldwide mass production of structural materials is based on the oxygen converter processing of pig iron via oxidation smelting into steel. The problem of oxidation smelting of cast iron in the oxygen converter is metal decarburisation. However, during oxygen

lancing of the iron melt, not only the oxidation of the carbon of the cast iron occurs, but also the oxidation of a significant part of iron and the complete oxidation of the valuable alloying metals with formation of metal oxides, which are transported into the converter slag. In converter smelting, not only the formation of metal-containing slags occurs, but a significant mass of sludges with concentration of metals many times higher than in slag. They are also accumulated in dumps.

Metal-containing wastes accumulation is a problem nowadays not only for the environmental security of the regions, but also as a secondary source of raw materials for the production of metal [1].

Pursuance of the most low-cost use of these wastes is associated with their return, if possible, according to the current scheme of the metallurgical cycle, in particular, to the agglomeration process. However, the possibility of introducing dispersed metal-containing waste into the sintering charge is limited and the mass of the incandescent metal-containing waste is expanding every year.

Analyzing new theoretical propositions [2] and the organization of the processes of mini production of iron and steel [3-5], one may come to the conclusion that the last word of science is related not only to the existing principle of the preparation of the agglomerated oxide raw material and its reducing melting, but a new principle of preparation of disperse metal-containing raw materials and its reduction-smelting processing.

Such an approach opens the prospect of not only the full use of current and accumulated waste, but also the direct production of high-quality steels and alloys from them.

The principle of agglomerated oxide raw material (agglomerate, pellets) preparation is based mainly on the use of HRG as a reducing agent, which requires high gas permeability of the burden layer. The very organization of the reduction processes in countercurrent of the agglomerated charge column and HRG from the position of the process kinetics has a number of significant drawbacks. The commonly advertised adsorption-catalytic mechanism (ACM) [6] is not a determining factor in the realization of metal reduction. On the contact surface between the agglomerated raw material and HRG, the metal reduction mechanism is associated with a topochemical mass transfer regime [7], by the successive phase transformation of the oxides into a metallic state from the surface to the center of the pieces. Such a sequence of the process is limited by the slowest contact-diffusion mechanism.

In the processes of metallization of dispersed metal-containing waste, HRG cannot be used as a reducing agent. The most effective reducing agent is solid carbon, which does not require gas permeability of the layer, while at the same time provides a high rate of reaction depending on the value of the RSC coefficient (reaction-contact surface). The value of the RSC in the 1,0 mm thick dispersible waste layers reaches up to 20,000 m²/kg, and below 1,0 mm can reach up to 30,000 m²/kg.

Conditions for the realization of direct reduction of metals is, first of all, the uniform distribution of a carbon-containing reagent of a similar reaction in a layer of dispersed oxide waste. Based on this principle of charge preparation, experimental studies were carried out.

Experimental procedure. In the experimental studies, metal-containing and carbon-containing industrial wastes - converter sludge and coal sludge chemical compositions of which are presented in table 1 from the JSC "ArcelorMittal Temirtau" metallurgical enterprise were used.

It can be seen from the composition of the initial slimes that the content of the basic CaO oxide is almost 4-times higher than the concentration of acid oxides (SiO₂+Al₂O₃) in fluxes. Hence it can be seen that phosphorus and sulfur with concentration of 0,5 and 0,2% are in the form of chemical compounds of Ca₃(PO₄)₂ and CaS, respectively. Coal sludge also contains rather high concentration of slag-forming oxides - SiO₂ и Al₂O₃.

Table 1 – Chemical composition of initial components

Name of components	Chemical composition, %									
	Fe _{com}	FeO	MnO	SiO ₂	Al ₂ O ₃	CaO	MgO	S	P	C
Converter sludge	60,3	12,5	1,75	2,54	3,25	22,0	2,32	0,20	0,50	2,65
Coal sludge	–	–	–	18,2	7,65	2,32	0,72	0,18	0,05	52,3

Therefore, the initial sludge was pretreated to remove a part of the slag-forming gangue. Both sludges were enriched: converter sludge - by magnetic separation, and coal sludge - by gravity concentration.


In the dry coal sludge the specific weight of slag-forming oxide particles (SiO_2 , Al_2O_3 , CaO , MgO) is, on average, five times greater than the specific mass of solid carbon particles. Within respective limits, their hovering velocities vary, i.e. particles removal rate. These variations were used for separation in the wind tube, which was charged with dry coal sludge and the layer was purged with air at a rate of 5,0-6,0 m/s, which corresponds to fine carbon particles hovering velocity. Smaller and lighter particles are blown through a special vent and enters the second container - dust collector. The trapped dust mainly contained carbon particles.

The compositions of enriched converter and coal sludges are presented in table 2.

Table 2 – Chemical composition of processed converter and coal sludges

Name of components	Chemical composition, %									
	Fe _{com}	FeO	MnO	SiO ₂	Al ₂ O ₃	CaO	Mg	S	P	C
Converter sludge	71,25	14,75	1,93	1,51	1,92	12,75	1,33	0,02	0,12	2,95
Coal sludge	–	–	–	6,86	2,87	0,87	0,27	0,06	0,02	65,74

As can be seen from the results of the analysis presented in table 2, rather qualitative components - iron ore concentrate with high iron content and a carbonaceous reagent with a carbon content of 65% were obtained from the initial converter and coal sludges. Only phosphorus content in the concentrate is much higher than the allowable rate. However, it should be stipulated that high concentration of basic CaO oxide in converter sludge is associated with the technology of dephosphorization of pig iron in an oxygen converter in which oxidized phosphorus P_2O_5 is bound by calcium oxide according to the following reactions:



As can be seen, phosphorus dissolved in the cast iron, oxidized in P_2O_5 by reaction (1), binds firmly to calcium phosphate by reaction (2). Considering the high chemical strength of $\text{Ca}_3(\text{PO}_4)_2$, in the organization of subsequent reduction and smelting processes, it is advisable to regulate the temperature-heat regime of phosphorus reduction. Based on this formulation of tasks, the following sequence of organization of the process was adopted.

1. Preparation of ore-coal mixture from converter and coal sludges.
2. Obtaining ore-coal pellets from the fine ore-coal mixture.
3. Metallization of ore-coal pellets.
4. Reduction smelting of metallized pellets and obtaining nature-alloyed steel.

Since solid carbon is used as the reducing agent, when preparing the ore, the coal mixture is based on the principle of complete reduction of the useful extractable metals of iron and manganese. Therefore, the stoichiometric consumption of the prepared coal sludge per unit of iron ore concentrate was determined according to the developed procedure, taking into account the successive phase transformation of oxides [8]. As a result of the performed calculations, the consumption of coal cuttings per unit of concentrate in the amount of 0,265 kg/kg was obtained. The ore-coal mixture consisted of the amount of prepared converter and coal sludges in the amount of $1 + 0,265 = 1,265$ kg. The resulting dispersed ore-coal mixture was thoroughly mixed, then ore-carbon pellets were obtained from the pellet granulator. An aqueous solution of nitrocellulose varnish was used as a binder. Mixing of converter and coal sludges inevitably leads to a change in the chemical composition of the mixture, in which the mass fraction of ore and coal parts was determined from the ratio $\gamma_p = 1,0 : 1,265 = 0,79$ and $\gamma_y = 0,265 : 1,265 = 0,21$. Based on these mass ratios, the average chemical composition of the mixture was determined, which is presented in Table 3.

Obtained crude pellets with fraction of 8,0-20,0 mm after drying at 400°C have acquired sufficient strength and have been prepared for metallization.

Since the pellets contain an increased concentration of phosphorus and a stoichiometric amount of carbon in choosing the temperature regime, not only the direct reduction of metals by carbon was taken into account, but also the possibility of limiting the transition of phosphorus to the metal. Here the favorable effect is due to the fact that phosphorus is completely in the compounds of calcium phosphate, from which it begins to recover only at temperatures above 1200 °C. Therefore, the metallization process was limited to heating to 1000-1100 °C.

The dried pellets with a mass of 200 g were placed in a sealed cell made of a quartz tube with a diameter Ø40 mm and introduced into the tubular furnace SUOL-044 12-M2, preheated to 550 °C, then heated at a rate of 10 °C/min. At 650 °C, the beginning of expelling of the gas - the reaction products of CO and CO₂ was recorded. When temperature reached 1100-1120 °C, a time delay of 25-30 minutes was observed until the gas expelling ceased, which meant the completion of the direct reduction of metals.

The chemical composition of ore-coal and metallized pellets is presented in table 3.

Table 3 – Chemical composition of ore-coal and metallized pellets

Name of pellets	Chemical composition, %										
	Fe _{com}	Fe _{met}	FeO	Mn	SiO ₂	Al ₂ O ₃	CaO	MgO	S	P	C
Ore-coal	56,29	–	11,65	1,18	2,63	2,12	10,25	1,107	0,036	0,10	16,13
Metallized	86,6	84,0	3,34	1,81	4,05	3,26	15,77	1,70	0,04	0,154	2,15

Samples of metallized materials together with the cell were removed from the furnace, cooled and further reloaded into a refractory crucible and installed in a "Tamman" melting furnace. The furnace was heated at a rate of 15-20 °C/min. In order to avoid secondary oxidation of the metallized pellets, the surface of the crucible was blown with neutral gas - argon. When the temperature reached 1600 °C, the pellets were completely transferred to the melt, which was drained into a refractory baking sheet.

The yield of metal was 68,0 g. from the initial 200 g. of ore-coal pelletized pellets. Analysis of metals obtained from two runs is provided in table 4.

Table 4 – Chemical composition of samples of molten metal

Metal samples	Chemical composition, %				
	[Mn]	[C]	[Si]	[S]	[P]
Test № 1	1,20	0,57	0,15	0,02	0,028
Test № 2	1,25	0,62	0,12	0,025	0,030

As can be seen from the results of the analysis, melted samples of metal are nature-alloyed steels. The content of contaminants - sulfur and phosphorus meets the technical requirements of high-quality steel.

Conclusion. On the basis of metal-containing and carbon-containing sludge of JSC "ArcelorMittal Temirtau", ore pelletized pellets with stoichiometric carbon content are obtained. Sequential processing of drying, metallization and reduction smelting made it possible to obtain in the final stage metal ingots, which in composition correspond to high-quality steel.

**С. М. Тлеугабулов¹, Д. И. Рыжонков²,
Н. Б. Айтбаев³, Г. М. Қойшина¹, Е. Көбеген³, Г. И. Сұлтамұрат³**

¹Қ. И. Сәтбаев атындағы Қазақ ұлттық техникалық зерттеу университеті (Сәтбаев Университеті),
Алматы, Қазақстан,

²Ұлттық технологиялық зерттеу университеті, Мәскеу, Ресей,

³Қарағанды мемлекеттік техникалық университеті, Қарағанды, Қазақстан

ҚҰРАМЫНДА МЕТАЛЛ БАР ӨНЕРКӘСІПТІК ҚАЛДЫҚТАРДЫ РЕДУКЦИЯЛАП БАЛҚЫТУ

Аннотация. Құрамында металл бар қалдықтардың жинақталуы бүгінгі таңда тек өңірлердің экологиялық қауіпсіздігі мәселесі ғана емес, сондай-ақ энергия мен ресурстарды үнемдеу саясатын есепке ала отырып, қара металлургия саласы дамуының жаңа парадигмасына (тікелей темір өндірісі) байланысты болуы керек.

Жұмыстың мақсаты: «АрселорМиттал Теміртау» АҚ металлургиялық комбинатының құрамында металл бар және көміртегі бар қалдықтар – конвертерлік шлам мен көмірді байыту шламдарын пайдалану.

Процесті ұйымдастыру кезектілігі мынадай: 1) конвертер және көмір шламдарынан кенді көмірлі қоспаны дайындау; 2) ұсақ кен көмірлі қоспадан кен көмірлі окатыштер алу; 3) кен көмірлі окатыштерді металлизациялау; 4) металданған окатыштерді редукциялап-балқыту және легіріленген болат алу.

Тотықсыздандырғыш реагент ретінде қатты көміртегі қабылданған-дықтан, кен көмірлі қоспаны дайындау кезінде темір мен марганец металдарынан алынған пайдалыларды толық тотықсыздандыру принципіне сүйенеміз. Сондықтан оксидтердің реттік-фазалық түрленуін ескерумен әзірленген әдістеме бойынша темір рудалы концентрат бірлігіне дайындалған көмір шламының стехиометриялық шығыны анықталды. Есептеулерді орындау нәтижесінде 0,265 кг/кг мөлшерінде концентрат бірлігіне кететін көмір шламының мөлшері алынды. Көмір кенді қоспа конвертерлік және көмір шламдарының сомасынан құралды.

«АрселорМиттал Теміртау» АҚ жағдайындағы құрамында металл бар және көміртегі бар шламдарының негізінде көміртегінің стехиометрлік құрамымен көмірлі окатыштер дайындау ұйымдастырылды. Оларды ретімен өңдеу, кептіру, металдандыру және редукциялап-балқыту соңында сапалы болаттың құрамына сәйкес келетін металл құймасын алуға мүмкіншілік береді.

Түйін сөздер: құрамында металл бар қалдықтар, конвертерлік шлам, көмір шламы, металдау, окатыш, болат, көміртегі, фосфор, редукциялау, балқыту, кристалдану.

**С. М. Тлеугабулов¹, Д. И. Рыжонков²,
Н. Б. Айтбаев³, Г. М. Қойшина¹, Е. Көбеген³, Г. И. Сұлтамұрат³**

¹Казахский национальный исследовательский технический университет им. К. И. Сатпаева
(Сатпаев Университет), Алматы, Казахстан,

²Национальный исследовательский технологический университет (МИСиС), Москва, Россия,

³Карагандинский государственный технический университет, Караганда, Казахстан

ВОССТАНОВИТЕЛЬНАЯ ПЛАВКА МЕТАЛЛОСОДЕРЖАЩИХ ПРОМЫШЛЕННЫХ ОТХОДОВ

Аннотация. Накопление металлосодержащих отходов сегодня является проблемой не только экологической безопасности регионов, но и должно быть связано с новой парадигмой развития черной металлургии (прямое получение железа) с учетом политики энерго- и ресурсосбережения технологий.

Цель работы: использовать металлосодержащие и углеродсодержащие промышленные отходы металлургического комбината АО «АрселорМиттал Темиртау» - конвертерный шлам и шлам углеобогащения.

Последовательность организации процесса состоит из: 1) подготовка рудоугольной смеси из конвертерного и угольного шламов; 2) получение рудоугольных окатышей из мелкий рудо угольной смеси; 3) металлизация рудоугольных окатышей; 4) восстановительная плавка металлизированных окатышей и получение природолегированной стали.

В качестве восстановительного реагента принят твердый углерод, при подготовке рудо угольной смеси исходим из принципа полного восстановления полезных извлекаемых металлов железа и марганца. Поэтому был определен стехиометрический расход подготовленного угольного шлама на единицу железорудного

концентрата по разработанной методике с учетом последовательно-фазового превращения оксидов. В результате выполненных расчетов получен расход угольного шлама на единицу концентрата в количестве 0,265 кг/кг. Рудоугольная смесь состояла из суммы подготовленных конвертерных и угольных шламов.

На базе металлсодержащих и углеродсодержащих шламов АО «АрселорМиттал Темиртау» организована подготовка рудоугольных окатышей со стехиометрическим содержанием углерода. Последовательная обработка сушка, металлизация и восстановительная плавка позволила получить на завершающей стадии слитки металла, которые по составу соответствуют качественной стали.

Ключевые слова: металлсодержащий отход, конвертерный шлак, угольный шлак, металлизация, окатыш, сталь, углерод, фосфор, восстановление, плавка, кристаллизация.

Information about authors:

Tleugabulov Suleiman, doctor of technical science, academician NEA of the RK, Professor of the Department «Metallurgy and Mineral Processing" Kazakh National Research Technical University named after K. I. Satpayev (Satpayev University), Almaty, Kazakhstan; suleiman_70@mail.ru; <http://orcid.org/0000-0002-2006-6950>

Ryzhankov Dmitriy, doctor of technical science, academician RANS, professor of the Department "Functional Nanosystems and High-Temperature Materials", National University of Science and Technology (MISIS), Moscow, Russia; diryzhonkov@mail.ru; <http://orcid.org/0000-0002-3833-7931>

Aytbayev Nurlan, PhD student. Department «Nanotechnology and metallurgy», Karaganda State Technical University, Kazakhstan; nurlan_2303@mail.ru; <https://orcid.org/0000-0002-7469-4442>

Koishina Gulzada, doctor PhD. Department «Metallurgy and Mineral Processing" Kazakh National Research Technical University named after K. I. Satpayev (Satpayev University), Almaty, Kazakhstan; gulzada.koishina@mail.ru; <http://orcid.org/0000-0003-0592-3843>

Sultamurat Gulmira, candidate of Technical Sciences. Department «Nanotechnology and metallurgy», Karaganda State Technical University, Kazakhstan; sultamurat_gi@mail.ru; <https://orcid.org/0000-0002-0206-1638>

REFERENCES

[1] Shomanova Z.K. et al. Study of composition of waste from metallurgy production aimed in use them as active phases of catalysts for hydrocarbon raw materials refining // News of the National Academy of Sciences of the Republic of Kazakhstan. Series of geology and technology sciences. **2017**. 6(426): 195-200. <https://doi.org/10.32014/2018.2518-170X> (in Eng.).

[2] Tleugabulov S.M. Theoretical provisions of direct production of steel by reduction smelting // International Scientific and Technical and Production Journal "Steel". **2003**. N 8. P. 18-20.

[3] Smirnov N.A. About introduction of innovative technology for direct iron reduction // Journal of Electrometallurgy. **2011**. N 4. P. 46-47.

[4] Usachayev A.B., Leherzak V.E., Balasanov A.V. Reduction of iron in the process of ROMELT // Journal of Ferrous Metals. **2000**. N 12. P. 14-21.

[5] 1B124. Midrex and Kobe Develop New Direct Iron Reduction Process // Iron and Steelmaker. **1996**.

[6] Chufarov G.I., Tatievskaya E.G. Adsorption-catalytic theory of the reduction of metal oxides // Problems of metallurgy. M.: USSR AS, **1953**. P. 15-32.

[7] Rybkin V.S., Leont'ev L.I., Leushin V.N., Evstyugin S.N., Gorbachev V.A. Systems for reducing Kachkanarsk pellets // Steel in Translation. **2008**. Vol. 38, N 7. P. 550-555. DOI 10.3103/S0967091208070139.

[8] Tleugabulov S.M. Metallurgical processes theory. Almaty: edition of the EPB for educational and methodological literature. **2007**. 351 p. ISBN-9965-495-57-2.

**Publication Ethics and Publication Malpractice
in the journals of the National Academy of Sciences of the Republic of Kazakhstan**

For information on Ethics in publishing and Ethical guidelines for journal publication see <http://www.elsevier.com/publishingethics> and <http://www.elsevier.com/journal-authors/ethics>.

Submission of an article to the National Academy of Sciences of the Republic of Kazakhstan implies that the described work has not been published previously (except in the form of an abstract or as part of a published lecture or academic thesis or as an electronic preprint, see <http://www.elsevier.com/postingpolicy>), that it is not under consideration for publication elsewhere, that its publication is approved by all authors and tacitly or explicitly by the responsible authorities where the work was carried out, and that, if accepted, it will not be published elsewhere in the same form, in English or in any other language, including electronically without the written consent of the copyright-holder. In particular, translations into English of papers already published in another language are not accepted.

No other forms of scientific misconduct are allowed, such as plagiarism, falsification, fraudulent data, incorrect interpretation of other works, incorrect citations, etc. The National Academy of Sciences of the Republic of Kazakhstan follows the Code of Conduct of the Committee on Publication Ethics (COPE), and follows the COPE Flowcharts for Resolving Cases of Suspected Misconduct (http://publicationethics.org/files/u2/New_Code.pdf). To verify originality, your article may be checked by the Cross Check originality detection service <http://www.elsevier.com/editors/plagdetect>.

The authors are obliged to participate in peer review process and be ready to provide corrections, clarifications, retractions and apologies when needed. All authors of a paper should have significantly contributed to the research.

The reviewers should provide objective judgments and should point out relevant published works which are not yet cited. Reviewed articles should be treated confidentially. The reviewers will be chosen in such a way that there is no conflict of interests with respect to the research, the authors and/or the research funders.

The editors have complete responsibility and authority to reject or accept a paper, and they will only accept a paper when reasonably certain. They will preserve anonymity of reviewers and promote publication of corrections, clarifications, retractions and apologies when needed. The acceptance of a paper automatically implies the copyright transfer to the National Academy of Sciences of the Republic of Kazakhstan.

The Editorial Board of the National Academy of Sciences of the Republic of Kazakhstan will monitor and safeguard publishing ethics.

Правила оформления статьи для публикации в журнале смотреть на сайте:

[www:nauka-nanrk.kz](http://www.nauka-nanrk.kz)

ISSN 2518-170X (Online), ISSN 2224-5278 (Print)

<http://www.geolog-technical.kz/index.php/en/>

Верстка Д. Н. Калкабековой

Подписано в печать 06.02.2019.

Формат 70x881/8. Бумага офсетная. Печать – ризограф.

16,7 п.л. Тираж 300. Заказ 1.