

**ISSN 2518-170X (Online),
ISSN 2224-5278 (Print)**

ҚАЗАҚСТАН РЕСПУБЛИКАСЫ
ҰЛТТЫҚ ҒЫЛЫМ АКАДЕМИЯСЫНЫҢ

Қ. И. Сәтпаев атындағы Қазақ ұлттық техникалық зерттеу университеті

Х А Б А Р Л А Р Ы

ИЗВЕСТИЯ

НАЦИОНАЛЬНОЙ АКАДЕМИИ НАУК
РЕСПУБЛИКИ КАЗАХСТАН
Казахский национальный исследовательский
технический университет им. К. И. Сатпаева

NEWS

OF THE ACADEMY OF SCIENCES
OF THE REPUBLIC OF KAZAKHSTAN
Kazakh national research technical university
named after K. I. Satpayev

SERIES
OF GEOLOGY AND TECHNICAL SCIENCES

5 (437)

SEPTEMBER – OCTOBER 2019

THE JOURNAL WAS FOUNDED IN 1940

PUBLISHED 6 TIMES A YEAR

ALMATY, NAS RK

NAS RK is pleased to announce that News of NAS RK. Series of geology and technical sciences scientific journal has been accepted for indexing in the Emerging Sources Citation Index, a new edition of Web of Science. Content in this index is under consideration by Clarivate Analytics to be accepted in the Science Citation Index Expanded, the Social Sciences Citation Index, and the Arts & Humanities Citation Index. The quality and depth of content Web of Science offers to researchers, authors, publishers, and institutions sets it apart from other research databases. The inclusion of News of NAS RK. Series of geology and technical sciences in the Emerging Sources Citation Index demonstrates our dedication to providing the most relevant and influential content of geology and engineering sciences to our community.

Қазақстан Республикасы Ұлттық ғылым академиясы "ҚР ҰҒА Хабарлары. Геология және техникалық ғылымдар сериясы" ғылыми журналының Web of Science-тің жаңаланған нұсқасы Emerging Sources Citation Index-те индекстелуге қабылданғанын хабарлайды. Бұл индекстелу барысында Clarivate Analytics компаниясы журналды одан әрі the Science Citation Index Expanded, the Social Sciences Citation Index және the Arts & Humanities Citation Index-ке қабылдау мәселесін қарастыруды. Web of Science зерттеушілер, авторлар, баспашилар мен мекемелерге контент тереңдігі мен сапасын ұсынады. ҚР ҰҒА Хабарлары. Геология және техникалық ғылымдар сериясы Emerging Sources Citation Index-ке енүі біздің қоғамдастық үшін ең өзекті және беделді геология және техникалық ғылымдар бойынша контентке адалдығымызды білдіреді.

НАН РК сообщает, что научный журнал «Известия НАН РК. Серия геологии и технических наук» был принят для индексирования в Emerging Sources Citation Index, обновленной версии Web of Science. Содержание в этом индексировании находится в стадии рассмотрения компанией Clarivate Analytics для дальнейшего принятия журнала в the Science Citation Index Expanded, the Social Sciences Citation Index и the Arts & Humanities Citation Index. Web of Science предлагает качество и глубину контента для исследователей, авторов, издателей и учреждений. Включение Известия НАН РК. Серия геологии и технических наук в Emerging Sources Citation Index демонстрирует нашу приверженность к наиболее актуальному и влиятельному контенту по геологии и техническим наукам для нашего сообщества.

Бас редакторы
э. ф. д., профессор, КР ҮГА академигі
И.К. Бейсембетов
Бас редакторының орынбасары
Жолтаев Г.Ж. проф., геол.-мин. ф. докторы
Редакция алқасы:

Абаканов Т.Д. проф. (Қазақстан)
Абишева З.С. проф., академик (Қазақстан)
Агабеков В.Е. академик (Беларусь)
Алиев Т. проф., академик (Әзірбайжан)
Бакиров А.Б. проф., (Қыргыстан)
Беспаев Х.А. проф. (Қазақстан)
Бишимбаев В.К. проф., академик (Қазақстан)
Буктуков Н.С. проф., академик (Қазақстан)
Булат А.Ф. проф., академик (Украина)
Ганиев И.Н. проф., академик (Тәжікстан)
Грэвис Р.М. проф. (АҚШ)
Ерғалиев Г.К. проф., академик (Қазақстан)
Жуков Н.М. проф. (Қазақстан)
Қожахметов С.М. проф., академик (Казахстан)
Конторович А.Э. проф., академик (Ресей)
Курскеев А.К. проф., академик (Қазақстан)
Курчавов А.М. проф., (Ресей)
Медеу А.Р. проф., академик (Қазақстан)
Мұхамеджанов М.А. проф., корр.-мүшесі (Қазақстан)
Нигматова С.А. проф. (Қазақстан)
Оздоев С.М. проф., академик (Қазақстан)
Постолатий В. проф., академик (Молдова)
Ракишев Б.Р. проф., академик (Қазақстан)
Сейтов Н.С. проф., корр.-мүшесі (Қазақстан)
Сейтмуратова Э.Ю. проф., корр.-мүшесі (Қазақстан)
Степанец В.Г. проф., (Германия)
Хамфери Дж.Д. проф. (АҚШ)
Штейнер М. проф. (Германия)

«ҚР ҮГА Хабарлары. Геология мен техникалық ғылымдар сериясы».

ISSN 2518-170X (Online),

ISSN 2224-5278 (Print)

Меншіктенуші: «Қазақстан Республикасының Ұлттық ғылым академиясы» РКБ (Алматы қ.).

Қазақстан республикасының Мәдениет пен ақпарат министрлігінің Ақпарат және мұрагат комитетінде 30.04.2010 ж. берілген №10892-Ж мерзімдік басылым тіркеуіне қойылу туралы куәлік.

Мерзімділігі: жылдан 6 рет.

Тиражы: 300 дана.

Редакцияның мекенжайы: 050010, Алматы қ., Шевченко көш., 28, 219 бөл., 220, тел.: 272-13-19, 272-13-18,
<http://www.geolog-technical.kz/index.php/en/>

© Қазақстан Республикасының Ұлттық ғылым академиясы, 2019

Редакцияның Қазақстан, 050010, Алматы қ., Қабанбай батыра көш., 69а.

мекенжайы: Қ. И. Сәтбаев атындағы геология ғылымдар институты, 334 бөлме. Тел.: 291-59-38.

Типографияның мекенжайы: «Аруна» ЖҚ, Алматы қ., Муратбаева көш., 75.

Г л а в н ы й р е д а к т о р
д. э. н., профессор, академик НАН РК
И. К. Бейсембетов
Заместитель главного редактора
Жолтаев Г.Ж. проф., доктор геол.-мин. наук

Р е д а к ц и о н а я к о л л е г и я:

Абаканов Т.Д. проф. (Казахстан)
Абишева З.С. проф., академик (Казахстан)
Агабеков В.Е. академик (Беларусь)
Алиев Т. проф., академик (Азербайджан)
Бакиров А.Б. проф., (Кыргызстан)
Беспаев Х.А. проф. (Казахстан)
Бишимбаев В.К. проф., академик (Казахстан)
Буктуков Н.С. проф., академик (Казахстан)
Булат А.Ф. проф., академик (Украина)
Ганиев И.Н. проф., академик (Таджикистан)
Грэвис Р.М. проф. (США)
Ергалиев Г.К. проф., академик (Казахстан)
Жуков Н.М. проф. (Казахстан)
Кожахметов С.М. проф., академик (Казахстан)
Конторович А.Э. проф., академик (Россия)
Курскеев А.К. проф., академик (Казахстан)
Курчавов А.М. проф., (Россия)
Медеу А.Р. проф., академик (Казахстан)
Мухамеджанов М.А. проф., чл.-корр. (Казахстан)
Нигматова С.А. проф. (Казахстан)
Оздоев С.М. проф., академик (Казахстан)
Постолатий В. проф., академик (Молдова)
Ракишев Б.Р. проф., академик (Казахстан)
Сеитов Н.С. проф., чл.-корр. (Казахстан)
Сейтмуратова Э.Ю. проф., чл.-корр. (Казахстан)
Степанец В.Г. проф., (Германия)
Хамфери Дж.Д. проф. (США)
Штейнер М. проф. (Германия)

«Известия НАН РК. Серия геологии и технических наук».

ISSN 2518-170X (Online),

ISSN 2224-5278 (Print)

Собственник: Республикаинское общественное объединение «Национальная академия наук Республики Казахстан (г. Алматы)

Свидетельство о постановке на учет периодического печатного издания в Комитете информации и архивов Министерства культуры и информации Республики Казахстан №10892-Ж, выданное 30.04.2010 г.

Периодичность: 6 раз в год

Тираж: 300 экземпляров

Адрес редакции: 050010, г. Алматы, ул. Шевченко, 28, ком. 219, 220, тел.: 272-13-19, 272-13-18,
<http://nauka-nanrk.kz/geology-technical.kz>

© Национальная академия наук Республики Казахстан, 2019

Адрес редакции: Казахстан, 050010, г. Алматы, ул. Кабанбай батыра, 69а.

Институт геологических наук им. К. И. Сатпаева, комната 334. Тел.: 291-59-38.

Адрес типографии: ИП «Аруна», г. Алматы, ул. Муратбаева, 75

Editor in chief
doctor of Economics, professor, academician of NAS RK

I. K. Beisembetov

Deputy editor in chief

Zholtayev G.Zh. prof., dr. geol-min. sc.

Editorial board:

Abakanov T.D. prof. (Kazakhstan)
Abisheva Z.S. prof., academician (Kazakhstan)
Agabekov V.Ye. academician (Belarus)
Aliyev T. prof., academician (Azerbaijan)
Bakirov A.B. prof., (Kyrgyzstan)
Bespayev Kh.A. prof. (Kazakhstan)
Bishimbayev V.K. prof., academician (Kazakhstan)
Buktukov N.S. prof., academician (Kazakhstan)
Bulat A.F. prof., academician (Ukraine)
Ganiyev I.N. prof., academician (Tadzhikistan)
Gravis R.M. prof. (USA)
Yergaliев G.K. prof., academician (Kazakhstan)
Zhukov N.M. prof. (Kazakhstan)
Kozhakhmetov S.M. prof., academician (Kazakhstan)
Kontorovich A.Ye. prof., academician (Russia)
Kurskeyev A.K. prof., academician (Kazakhstan)
Kurchavov A.M. prof., (Russia)
Medeu A.R. prof., academician (Kazakhstan)
Muhamedzhanov M.A. prof., corr. member. (Kazakhstan)
Nigmatova S.A. prof. (Kazakhstan)
Ozdoyev S.M. prof., academician (Kazakhstan)
Postolatii V. prof., academician (Moldova)
Rakishev B.R. prof., academician (Kazakhstan)
Seitov N.S. prof., corr. member. (Kazakhstan)
Seitmuratova Ye.U. prof., corr. member. (Kazakhstan)
Stepanets V.G. prof., (Germany)
Humphery G.D. prof. (USA)
Steiner M. prof. (Germany)

News of the National Academy of Sciences of the Republic of Kazakhstan. Series of geology and technology sciences.

ISSN 2518-170X (Online),

ISSN 2224-5278 (Print)

Owner: RPA "National Academy of Sciences of the Republic of Kazakhstan" (Almaty)

The certificate of registration of a periodic printed publication in the Committee of information and archives of the Ministry of culture and information of the Republic of Kazakhstan N 10892-Ж, issued 30.04.2010

Periodicity: 6 times a year

Circulation: 300 copies

Editorial address: 28, Shevchenko str., of. 219, 220, Almaty, 050010, tel. 272-13-19, 272-13-18,
<http://nauka-namrk.kz/geology-technical.kz>

© National Academy of Sciences of the Republic of Kazakhstan, 2019

Editorial address: Institute of Geological Sciences named after K.I. Satpayev
69a, Kabanbai batyr str., of. 334, Almaty, 050010, Kazakhstan, tel.: 291-59-38.

Address of printing house: ST "Aruna", 75, Muratbayev str, Almaty

NEWS

OF THE NATIONAL ACADEMY OF SCIENCES OF THE REPUBLIC OF KAZAKHSTAN

SERIES OF GEOLOGY AND TECHNICAL SCIENCES

ISSN 2224-5278

Volume 5, Number 437 (2019), 223 – 228

<https://doi.org/10.32014/2019.2518-170X.146>

UDC 625.7/8:691.16

M. Zh. Zhurinov¹, B. B. Teltayev², A. A. Kalybai²¹JSC “D. V. Sokolskiy Institute of Fuel, Catalysis and Electrochemistry”, Almaty, Kazakhstan,²JSC “Kazakhstan Highway Research Institute”, Almaty, Kazakhstan.

E-mail: nanrk.mzh@mail.ru, ao_kazdornii@mail.ru

CHARACTERISTICS OF ROAD BITUMEN MODIFIED WITH CARBON NANOPOWDER

Abstract. In the paper the improvement of low temperature properties of blown road bitumens by means of modification with a carbon nanopowder is shown. The bitumens of grade BND 70/100 and BND 100/130 have been produced by the Pavlodar petrochemical plant. The nanopowder has been obtained from a coal in the “Saryadyr” deposit (“ON-Olzha” corporation). Stiffness of the bitumens has been measured by a bending beam rheometer. Group chemical composition of the bitumens has been determined by the “Gradient” chromatograph. It was found that the Fraas point of the modified bitumens after short term aging on the RTFO method is not less than of the bitumen in non-modified and non-aged condition. Stiffness of the modified bitumen is considerably decreased at low temperatures (44%, 38% and 28% at the temperatures of -24 °C, -30 °C and -36 °C respectively). It has been stated that modification of the bitumens with the carbon nanopowder transforms the resins into compacted asphaltenes and decompactified oils consuming little energy for the process.

Key words: bitumen, carbon nanopowder, Fraas point, bending beam rheometer, stiffness, group chemical composition.

Introduction. The results of numerous investigations [1-10] show that conventional bitumens produced in plants do not practically always satisfy the requirements of operational conditions (including climatic ones) in many countries of the world, especially in the regions with sharp continental climate. As a rule to improve bitumens quality they are modified with polymers. Addition of polymers varies considerably the characteristics (physical and mechanical, rheological, etc.) of bitumens [11-13].

Due to what the abovementioned variations occur for bitumens characteristics at their modification with polymers? The answer should be searched, first of all, in variation of chemical composition of binders. Usually the researchers confine themselves only to physical and mechanical and rheological characteristics at the analysis of polymer type and content effect on bituminous binders properties, i.e. their chemical composition is not considered.

Table 1 represents the results for determination of group chemical composition of the neat bitumen of grade BND 100/130 and polymer bitumen binders manufactured by addition of various polymers into the bitumen. The neat bitumen has been produced by Pavlodar petrochemical plant (PPCP) from crude oil of Western Siberia by method of direct oxidation. The group chemical compositions of the basic neat bitumen and the polymer modified bitumens were determined in the laboratory of the Kazakhstan Highway Research Institute (KazdorNII) by method of adsorptive chromatography on Gradient M chromatograph [14, 15].

As the data of the table 1 show, without dependence on type and content of polymers, the bitumen modification is followed by the decrease of light components content (oils) and the increase of heavier components content (resins and asphaltenes). The increase of asphaltenes content due to the decrease of oils in the composition of the bitumen of grade BNS 70/100 (PPCP) at short-term and long-term aging has been determined in the work [14].

Table 1 – Group chemical composition of the neat bitumen of grade BND 100/130 and the polymer bituminous binders

Name of chemical compounds	Bitumen BND 100/130	Name and content of polymers				
		Bitumen BND 100/130 + KUMHO KTP (SBS) (Korea) – 6.0%	Bitumen BND 100/130 + Interchi-mica SBS – 4%	Bitumen BND 100/130 + SBS (L 30-01 A) – 3%	Bitumen BND 100/130 + Elvaloy AM – 2%	Bitumen BND 100/130 + Butonal NS 198 – 3%
Parafinonaftenes	21.9	16.7	16.35	15.6	16.1	14.45
Aromatics light	8.0	8.2	9.1	6.95	7.55	8.35
Aromatics middle	3.51	8.1	7.6	5.5	6.0	5.75
Aromatics heavy	22.1	21.3	18.5	21.8	23.7	25.15
Resins 1	6.6	7.5	6.7	8.45	9.05	8.35
Resins 2	24.1	24.0	27.4	21.7	22.3	21.35
Asphaltenes	13.8	15.2	15.4	20.0	15.3	16.65
Group chemical composition						
Oils	55.51	54.3	51.5	49.85	53.35	53.7
Resins	30.7	31.5	34.1	30.15	31.35	29.7
Asphaltenes	13.8	15.2	15.4	20.0	15.3	16.65

Thus, one can conclude that as at thermal aging as well as at polymer modification the following variation for group chemical composition of bitumen occurs: content of more light components (oils) is decreased and the content of heavier components (asphaltenes) is increased, and the content of intermediate components (resins) remains constant or it is also increased.

At present the possibility has been shown for application of nanoparticles of different structure as functional additives for bitumens [16]. Meanwhile, carbon nanoparticles are the closest to bitumen, as a component of petrol. It is considered that in this case the effect of modification will be a maximal one [17-19].

Materials and methods. Bitumens of grades BND 70/100 and BND 100/130 produced by PPCP have been taken for investigation of the impact of carbon nanopowder content on a group chemical composition. Nanopowder has been manufactured from a coal of ‘Saryadyr’ deposit belonging to “Corporation “ON-Olzha” LLP (Akmola region, Kazakhstan), and it has dimensions of 150-200 nm.

For the purpose of provision of the uniform distribution of the nanopowder particles in bitumen the nanopowder has been first dispersed in kerosene through the action of ultrasound with the frequency of 20 kHz for 5 minutes at a room temperature. Then the dispersed solution (kerosene+nanopowder) has been added to the bitumen at the temperature of 160 °C and constant stirring for 30 minutes. In such a way the samples of the nanocarbon bituminous binder (NCBB) have been prepared with the content of the carbon nanopowder from 0.1 to 2.0 % by weight.

Rational quantity of the nanopowder was determined according to the indicators of the bitumen resistance to aging. Bitumen “is aged” in the process of preparation of a hot asphalt concrete mix, light fractions are volatilized, bitumen becomes more brittle, less frost resistant.

The following main standard indicators for NCBB have been determined by appropriate methods of laboratory tests: needle penetration depth at the temperature of 25 °C under the standard ST RK 1226 [20], softening point on ring and ball under the standard ST RK 1227 [21], ductility at the temperature of 25 °C under the standard ST RK 1374 [22], Fraas point under the standard ST RK 1229 [23].

Aging of a binder at stirring of an asphalt concrete mix in a mixing device and during its laying occurs in conditions of a high temperature and air inflow. To model this form of aging the method of rolling of a thin film in the oven (RTFO) is used under the standard ST RK 1224 [24] and AASHTO T 240 [25].

To model the aging in the process of operation the accelerated method of aging is used in the device PAV under high pressure and at a high temperature for 20 hours under standard ASTM D 6521 [26]. The samples of a binder aged in PAV have already been subjected to aging under method RTFO. Binder

residue after aging under method PAV represents the binder subjected to the action of all the factors of the environment which it has during production of an asphalt concrete mix and operation of an asphalt concrete pavement.

In accordance with the Technical system Superpave the low temperature stability of bituminous binders is evaluated under the stiffness modulus value, determined at load duration of 60 seconds under the standard ASTM D 6648 [27] on a bending beam rheometer (BBR). In this work the stiffness modulus of the neat bitumen and NCBB was determined at the temperatures of -24 °C, -30 °C and -36 °C.

Group chemical compositions of the original and the nanomodified bitumens were determined on the chromatograph "Gradient".

Results and discussion.

Standard indicators. Main standard indicators of the bitumen and NCBB, determined under the abovementioned standards, are represented in table 2.

Table 2 – Main standard indicators of the neat bitumen and NCBB

Indicators	Content of nanopowder, %								
	Neat bitumen	Neat bitumen after aging (RTFO)	0.1	0.2	0.3	0.5	0.7	1.0	2.0
Depth of needle penetration at 25°C, 0.1 mm	75	55	47	61	62	59	59	64	61
Softening point, °C	47.5	51	55	53.5	53	53	52	51	51
Ductility at 25°C, cm	118	69	41	53.5	45	32	54	31	51
Fraas point, °C	-28.5	-24.5	-27.1	-27.2	-26.9	-28.5	-28.0	-24.3	-27.6

The results of table 2 data analysis have shown that adding of the nanocarbon powder decreases ductility to 26 %; softening point is practically not changed, and depth of the needle penetration is increased for 16 %.

It should be specially noted that bitumen aging under the method RTFO increases Fraas point for 4°C from -28.5°C to -24.5°C, and adding of the nanocarbon powder reduces Fraas point and already with the nanopowder content of 0.5 % the Fraas point of the neat bitumen is recovered, i.e. becomes equal to -28.5°C.

Stiffness. Table 3 gives stiffness modulus values for the neat bitumen and NCBB at lower temperatures, obtained by testing at BBR.

Table 3 – Stiffness modulus of the neat bitumen and NCBB at low temperatures

Temperature, °C	Content of nanopowder, %		
	0	0.5	2.0
-24	104.21	-24	104.21
-30	220.11	-30	220.11
-36	322.50	-36	322.50

As it is seen the nanopowder decreases considerably the stiffness modulus of the bitumen, i.e. increases low temperature stability. Modification effect is especially clearly shown with the content of the nanopowder of 0.5 %. So, the stiffness modulus of the bitumen with such concentration of the nanopowder at the temperatures of -24 °C, -30 °C and -36°C is 46 MPa (44.1 %), 83 MPa (37.7 %) and 91 MPa (28.2 %) respectively.

Thus, one can conclude that modification of the bitumen of grade BND 70/100 by the nanocarbon powder increases considerably its low temperature stability.

Group chemical composition. The obtained data on group chemical composition of the original bitumen and its modified samples have been tabulated into table 4.

Table 4 – Group chemical composition of the neat bitumen and NCBB

Bitumen	Asphal-tenes, %	Resins, %			Oils, %				
		Petrol-benzol	Spiritus-benzol	Sum of resins	Paraffin-naphthene	Light aromatic	Middle aromatic	Heavy aromatic	Sum of oils
BND 100/130 RTFO	11.8	24.5	20.4	44.9	20.6	3.6	4.3	14.9	43.4
BND 100/130 RTFO + 0.5% NANO	17.0	15.2	19.2	34.4	23.3	5.1	4.5	15.7	48.6
BND 100/130 RTFO + 0.7% NANO	17.8	17.0	16.6	33.6	23.6	4.3	4.6	16.1	48.6
BND 100/130 RTFO + 2.0% NANO	20.8	10.7	18.0	28.7	23.1	5.5	5.3	16.7	50.6

Progressing decrease of resins content with aggregate portion increase from 0.5% to 2.0% is seen from Table 4. At 2.0% of the added nanopowder portion the resins content is decreased for 16.2% by weight and the content of the asphaltenes and oils is increased for 9.0% and 7.2% by weight respectively.

Conclusion.

1. The possibility has been shown for considerable improvement of low temperature characteristics for road bitumens by their modification with a nanopowder from a coal: Fraas point of the modified bitumen after short-term aging under the RTFO method is not lower than for the original (non-aged) bitumen; stiffness is considerably decreased (at the temperatures of -24°C, -30°C and -36°C for 44%, 38% and 28% respectively).

2. Phenomenon previously unknown has been determined for differently directed weak energetic transformation of bitumen resins into compacted asphaltenes and non-compacted oils cumulatively forming a nanostructured bitumen with increased low temperature resistance during heating up to +160°C with addition of a nanopowder from a coal into a original bitumen.

М.Ж. Жұрынов¹, Б.Б. Телтаев² А.А. Қалыбай²,

¹«Д. В.Сокольский атындағы Жанармай, катализ және электрохимия институты» АҚ,

Алматы, Қазақстан,

²«Қазақстан жол ғылыми-зерттеу институты» АҚ, Алматы, Қазақстан

КӨМІР НАНОҮНТАҒЫ ҚОСЫЛҒАН ЖОЛ БИТУМЫНЫҢ СИПАТТАМАЛАРЫ

Аннотация. Мақалада тотықкан жол битумына көмір наноүнтағының қосу арқылы оның төменгі температуралық сипаттамаларын жақсарту мүмкіндігі көрсетілген. МЖБ 70/100 және МЖБ 100/130 маркалы битумдары Павлодар мұнай-химия зауытында өндірілген, ал өлшемі 150-200 нм наноүнтақ «ОН-Олжа» корпорациясының көмірінен алынды. Битумдардың төменгі температурадағы (-24 °C, -30 °C, -36 °C) қаттылығы иілгіш белгілі реометрмен өлшенді, топтық химиялық құрамы «Градиент» хроматографында анықталды. Наноүнтақ қосылған битумның RTFO әдісімен қысқа мерзімді ескірген күйіндегі морттық температурасы бастапкы (ескірмеген) битумдікінен кем еместігі көрсетілген.

Наноүнтақ қосылған битумның қаттылығы елеулі (-24 °C, -30 °C және -36 °C температураларда тиісінше 44%, 38%, 28 %) төмендейтіндігі анықталды. Бұрын белгісіз, битумға көмір наноүнтағының қосқанда шайырлардың тығыздалған асфальтендерге және қосылған майларға аз энергия шығынымен айналу құбылысы анықталды.

Түйін сөздер: битум, көмір наноүнтағы, морттық температурасы, иілгіш белгілі реометр, қаттылық, топтық химиялық құрам.

М. Ж. Журинов¹, Б. Б. Телтаев², А. А. Қалыбай²

¹АО «Институт топлива, катализа и электрохимии им. Д. В. Сокольского», Алматы, Казахстан,
²АО "Казахстанский дорожный научно-исследовательский институт" Алматы, Казахстан

ХАРАКТЕРИСТИКА ДОРОЖНОГО БИТУМА С НАНОЧАСТИЦАМИ УГЛЯ

Information about authors:

Zhurinov M. Zh., Doctor of Chemical Sciences, Professor, Academician, President of NAS RK, JSC "D. V. Sokslyk Institute of Fuel, Catalysis and Electrochemistry", Almaty, Kazakhstan; nanrk.mzh@mail.ru; <https://orcid.org/0000-0001-5314-1219>

Teltayev B. B., Doctor of Technical Sciences, Professor, Academician of NEA RK, President of JSC "Kazakhstan Highway Research Institute", JSC "Kazakhstan Highway Research Institute", ao_kazdornii@mail.ru; Almaty, Kazakhstan; <https://orcid.org/0000-0002-8463-9965>

Kalybay A.A. – Doctor of Physical and Mathematical Sciences, Academician of NEA RK, Scientific Consultant of JSC "Kazakhstan Highway Research Institute", Almaty, Kazakhstan; ao_kazdornii@mail.ru; <https://orcid.org/0000-0002-7646-8991>

REFERENCES

- [1] Teltayev B.B., Kaganovich E.V. Bitumen and asphalt concrete requirements improvement for the climatic conditions of the Republic of Kazakhstan // Proceedings of 24th World Road Congress. Mexico, 2011 (in Eng.).
- [2] Teltayev B., Kaganovich E. Thermal resistance of blown bitumens to the conditions of sharp-continental climate // Journal of Applied Sciences. 2012. Vol. 12, N 12.–P. 1297-1302 (in Eng.).
- [3] Teltayev B., Izmailova G., Amirbayev Ye. Rheological properties of oxidized bitumen with polymer additive // Journal of Applied Sciences. 2015. Vol. 15, N 1. P. 129-137 (in Eng.).
- [4] Superpave series No. 1. Performance graded asphalt binder specification and testing. Asphalt Institute: Lexington, MA, USA, 2003 (in Eng.).
- [5] Teltayev B., Kaganovich E., Izmailova G. Considering of climatic conditions for operation at selection of bitumen for asphalt concrete mixes // Science and Technology in road sphere. 2008. N 2. P. 17-20 (in Russ.).
- [6] Teltayev B., Kaganovich E., Izmailova G. To the matter of consideration of climatic conditions for operation at selection of bitumen for asphalt concrete mixes // Bulletin of KazdorNII. 2007. N 3/4. P. 61-68 (in Russ.).
- [7] King G.N., Radovskiy B.S. Properties of polymer bituminous binders and their test methods developed in the USA // Materials and structures. 2004. P. 16-27 (in Eng.).
- [8] Radovskiy B.S. Modern condition of development for Superpave method of designing of asphalt concrete mixes // Road machinery. 2008. P. 12-22 (in Eng.).
- [9] Radovskiy B.S., Teltayev B.B. Visco-elastic properties of asphalt based on penetration and softening point. Almaty: "Bilim" baspasy, 2013. 152 p. (in Russ.).
- [10] Radovskiy B.S., Teltayev B.B. Visco-elastic properties of asphalt based on penetration and softening point. Cham: Springer International Publishing AG, 2018. 115 p. (in Eng.).
- [11] Teltayev B., Amirbayev E. Evaluation of rheological characteristics for bituminous binders at various thermostatical durations // News of NAS RK. Series Geology and Technical Sciences. 2016. N 6. P. 162-172 (in Russ.).
- [12] Rossi C.O., Spadafora A., Teltayev B., Izmailova G., Amirbayev Ye., Bortolotti V. Polymer modified bitumen: Rheological properties and structural characterization // Colloids and Surfaces A: Physicochemical and Engineering Aspects. 2015. 480. P. 390-397 (in Eng.).
- [13] Teltayev B., Rossi C.O., Izmailova G., Amirbayev Ye., Elschibayev A. Evaluating the effect of asphalt binder modification on the low-temperature cracking resistance of hot mix asphalt // Case studies in Construction materials. 2019. N11. P. 1-13 (in Eng.).
- [14] Teltayev B., Rossi C.O., Ashimova S. Composition and rheological characteristics of bitumen in short-term and long-term aging // Magazine of Civil Engineering. 2018. Vol. 81, N 5. P. 93-101 (in Eng.).
- [15] Teltayev B., Seilkhanov T. NMR-spectroscopy determination of fragmentary composition of bitumen and its components // Eurasian Chemico-Technological Journal. 2018. N 20. P. 153-158 (in Eng.).
- [16] Zhang H., Zhu C., Yu J., Shi C., Zhang D. Influence of surface modification on physical and ultraviolet aging resistance of bitumen containing inorganic nanoparticles // Construction and building materials 98. 2015. P. 735-740 (in Eng.).

- [17] Amirkhanian A., Xiao F., Amirkhanian S. Evaluation of high temperature rheological characteristics of asphalt binders with carbon nanoparticles // Journal of testing and evaluation. 2011. Vol. 39, N 4. P. 1-9 (in Eng.).
- [18] Khattak M.J., Khattab A., Rizvi H.R., Zhang P. The impact of carbon nano-fiber modification on asphalt binder rheology // Construction and building materials. 2012. N 30. P. 257-264 (in Eng.).
- [19] Motlagh A.A., Kiasat A., Mirzaei E., Birgani F.O. Bitumen modification using carbon nanotubes // World applied sciences journal. 2012. Vol. 18, N 4. P. 594-599 (in Eng.).
- [20] ST RK 1226-2003. Bitumens and bituminous binders. Method for determination of needle penetration depth. Astana, 2003. 17 p. (in Russ.).
- [21] ST RK 1227-2003. Bitumens and bituminous binders. Determination of softening point by ring and ball method. Astana, 2003. 17 p. (in Russ.).
- [22] ST RK 1374-2005. Bitumens and bituminous binders. Method for determination of ductility. Astana, 2005. 16 p. (in Russ.).
- [23] ST RK 1229-2003. Bitumens and bituminous binders. Method for determination of Fraas point. Astana, 2003. 18 p. (in Russ.).
- [24] ST RK 1224-2003. Bitumens and bituminous binders. Method for determination of resistance to aging under the impact of heating and air environment. Astana, 2003. 24 p. (in Russ.).
- [25] AASHTO T 240-13. Standard test method for effect of heat and air on a moving film of asphalt binder (Rolling thin-film oven test). 2013 (in Eng.).
- [26] ASTM D 6521-08. Standard practice for accelerated aging of asphalt binder using pressurized aging vessel (PAV). 2008 (in Eng.).
- [27] ASTMD 6648-08. Standard test method for determining the flexural creep stiffness of asphalt binder using the bending beam rheometer (BBR). 2016 (in Eng.).

**Publication Ethics and Publication Malpractice
in the journals of the National Academy of Sciences of the Republic of Kazakhstan**

For information on Ethics in publishing and Ethical guidelines for journal publication see <http://www.elsevier.com/publishingethics> and <http://www.elsevier.com/journal-authors/ethics>.

Submission of an article to the National Academy of Sciences of the Republic of Kazakhstan implies that the described work has not been published previously (except in the form of an abstract or as part of a published lecture or academic thesis or as an electronic preprint, see <http://www.elsevier.com/postingpolicy>), that it is not under consideration for publication elsewhere, that its publication is approved by all authors and tacitly or explicitly by the responsible authorities where the work was carried out, and that, if accepted, it will not be published elsewhere in the same form, in English or in any other language, including electronically without the written consent of the copyright-holder. In particular, translations into English of papers already published in another language are not accepted.

No other forms of scientific misconduct are allowed, such as plagiarism, falsification, fraudulent data, incorrect interpretation of other works, incorrect citations, etc. The National Academy of Sciences of the Republic of Kazakhstan follows the Code of Conduct of the Committee on Publication Ethics (COPE), and follows the COPE Flowcharts for Resolving Cases of Suspected Misconduct (http://publicationethics.org/files/u2/New_Code.pdf). To verify originality, your article may be checked by the Cross Check originality detection service <http://www.elsevier.com/editors/plagdetect>.

The authors are obliged to participate in peer review process and be ready to provide corrections, clarifications, retractions and apologies when needed. All authors of a paper should have significantly contributed to the research.

The reviewers should provide objective judgments and should point out relevant published works which are not yet cited. Reviewed articles should be treated confidentially. The reviewers will be chosen in such a way that there is no conflict of interests with respect to the research, the authors and/or the research funders.

The editors have complete responsibility and authority to reject or accept a paper, and they will only accept a paper when reasonably certain. They will preserve anonymity of reviewers and promote publication of corrections, clarifications, retractions and apologies when needed. The acceptance of a paper automatically implies the copyright transfer to the National Academy of Sciences of the Republic of Kazakhstan.

The Editorial Board of the National Academy of Sciences of the Republic of Kazakhstan will monitor and safeguard publishing ethics.

Правила оформления статьи для публикации в журнале смотреть на сайте:

www:nauka-nanrk.kz

ISSN 2518-170X (Online), ISSN 2224-5278 (Print)

<http://www.geolog-technical.kz/index.php/en/>

Верстка Д. Н. Калкабековой

Подписано в печать 14.10.2019.
Формат 70x881/8. Бумага офсетная. Печать – ризограф.
15,0 п.л. Тираж 300. Заказ 5.